

Silver Alloyed Copper: CuAg0,10 is silver containing electrolytic tough pitch copper (ETP, CW013A, C116) - alloy. The absence of deoxidizers accounts for an electrical conductivity of 100 %.

Properties:

- Good electrical conductivity
- Good thermal conductivity
- Excellent corrosion resistance
- Good formability
- Recyclable
- Prone to hydrogen embrittlement in reducing atmosphere

Composition:

- Cu+ Ag min. 99,93 ppm
- Ag content 800 – 1200 ppm
- Oxygen content max. 400 ppm

Electrical conductivity:

High conductivity copper

- min 100 % IACS

According to EN: H040 min 100 % IACS, H065-90 min 98,3 % IACS, H110 min 96,6 % IACS

Typical applications:

- Continuous casting mould
- Engraving industry / graphic plates

Aurubis Finland Oy
Kuparitie
PL 60
28101 Pori
Puh. 02 626 6111
Fax. 02 626 5307

Info-pori@aurubis.com
www.aurubis.fi

Physical Properties, Tempers and Mechanical Properties:

Alloy Name	Cu-Ag0,10
European Standard Number	CW013A
UNS Code	C11600
Manufacturing Location	Pori
Density	8.9 g/cm ³ , 0.323 lb/in ³
Electrical Conductivity	min 100 % IACS
Thermal Conductivity	min 386 W/(m °K), 223 Btu/(ft hr °F)
Modulus of Elasticity	117 GPa, 17 X1000 ksi
Coef. of Thermal Exp. at 20 °C (68 °F)	17.6 10-6/°C, 9.8 10-6/°F
EN H040 / R200	
Tensile Strength Rm N/mm ²	200 - 250
Yield Strength (0.2 %) N/mm ²	max 100
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min - / 42
Hardness HV	40 - 65
EN H040 / R220	
Tensile Strength Rm N/mm ²	220 - 260
Yield Strength (0.2 %) N/mm ²	max 140
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 33 / 42
Hardness HV	40 - 65
EN H065 / R240	
Tensile Strength Rm N/mm ²	240 - 300
Yield Strength (0.2 %) N/mm ²	min 180
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 8 / 15
Hardness HV	65 - 95
EN H090 / R290	
Tensile Strength Rm N/mm ²	290 - 360
Yield Strength (0.2 %) N/mm ²	min 250
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 4 / 6
Hardness HV	90 - 110
EN H110 / R360	
Tensile Strength Rm N/mm ²	min 360
Yield Strength (0.2 %) N/mm ²	min 320
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 2 / -
Hardness HV	min 110

Other tempers - as ASTM - are available upon request.
 Data for information only not for purchase specification.
 Yield strength, Elongation and Hardness are typical values for each temper.