

Oxygen – Free Silver Copper, High Conductivity Copper (CW019A, C107) -alloy offers the high purity and absence of deoxidisers accounts for electrical conductivity of 100 % IACS as well as no susceptibility for hydrogen embrittlement.

Properties:

- High electrical conductivity min. 100 % IACS
- High thermal conductivity
- Good formability and weldability
- Excellent corrosion resistance
- Resists hydrogen embrittlement
- Low metal volatility in vacuum
- High scrap value

Composition:

- Cu + Ag min 99,99 %
- Ag 0.08 – 0.12 %
- Oxygen free, O2 max 10 ppm

Electrical conductivity:

High conductivity copper

- min 100 % IACS

According to EN: H040 min 100 % IACS, H065-90 min 98,3 % IACS, H110 min 96,6 % IACS

Typical applications:

- Engraving industry / graphic plates,
- Commutators

Aurubis Finland Oy
Kuparitie
PL 60
28101 Pori
Puh. 02 626 6111
Fax. 02 626 5307

Info-pori@aurubis.com
www.aurubis.fi

CuAg0,10(OF)

Physical Properties, Tempers and Mechanical Properties:

Alloy Name	CuAg0.10(OF)
European Standard Number	CW019A
UNS Code	C10700
Manufacturing Location	Pori
Density	8.9 g/cm ³ , 0.323 lb/in ³
Electrical Conductivity	min 100 % IACS
Thermal Conductivity	min 386 W/(m °K), 223 Btu/(ft hr °F)
Modulus of Elasticity	117 GPa, 17 X1000 ksi
Coef. of Thermal Exp. at 20 °C (68 °F)	17.6 10-6/°C, 9.8 10-6/°F
EN H040 / R200	
Tensile Strength Rm N/mm ²	200 - 250
Yield Strength (0.2 %) N/mm ²	max 100
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min - / 42
Hardness HV	40 - 65
EN H040 / R220	
Tensile Strength Rm N/mm ²	220 - 260
Yield Strength (0.2 %) N/mm ²	max 140
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 33 / 42
Hardness HV	40 - 65
EN H065 / R240	
Tensile Strength Rm N/mm ²	240 - 300
Yield Strength (0.2 %) N/mm ²	min 180
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 8 / 15
Hardness HV	65 - 95
EN H090 / R290	
Tensile Strength Rm N/mm ²	290 - 360
Yield Strength (0.2 %) N/mm ²	min 250
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 4 / 6
Hardness HV	90 - 110
EN H110 / R360	
Tensile Strength Rm N/mm ²	min 360
Yield Strength (0.2 %) N/mm ²	min 320
Elongation % A50 / A (0.1- < 2.5 mm/ 2.5 mm -)	min 2 / -
Hardness HV	min 110

Other tempers - as ASTM - are available upon request.
 Data for information only not for purchase specification.
 Yield strength, Elongation and Hardness are typical values for each temper.